



パーフロロフツ素ゴム<FFKM> AGC Perfluoroelastomer <FFKM>

NEW

AFLAS®を補完するラインアップを上市予定。(2006年中)

Coming soon.

参考データ Reference data

Physical Properties	Unit	
Tensile Strength	MPa	20.8
Elongation	%	190
100% Modulus	MPa	10.3
Hardness(ShoreA)	-	86
Specific Gravity	-	2.00
Compression Set*	%	14

*200°C×70h

